

PRODUCT INFORMATION

Hematite



AM2F Energy offers the highest quality hematite for use in the drilling process. Using hematite from **AM2F Energy** increases penetration rates as compared to the barite alone mud because of its 22% higher specific gravity.

In addition, the oil muds prepared with **AM2F Energy** hematite (conductor) exhibit lower electrical stability readings compared to those muds formulated with barite (non conductor).



ITEM

Mica Iron Oxide Pigment	
Color	Steel grey
Content of Fe ₂ O ₃	(max93%)
Specific Gravity g/cm ³	4.9-5.1
Size/Grains	200mesh-600mesh
Volatile (≤%) 105°C	0.8
Water Soluble (≤%)	0.5
pH Value	6-8
Oil Absorbtion (%)	9-14
Sieve Residue (≤%)	0.5
Content of SiO ₂ (≤%)	3.2
Moisture (≤%)	0.5



Use your QR reader here
to learn more about AM2F Energy

Product information herein is presented in good faith and believed to be accurate.
The information does not constitute a guarantee or warranty. Version 2.4